

Oil-resistance of Typical Transparent Material

◎ : Best suited ○ : Moderate × : Incompatible *1 May causes color migration of gasoline

	CNC Machining			SLA	Vacuum Casting
	Polycarbonate	Acrylic	Rigid PVC	TSR-829	Hei-Cast 3744
Gasoline	◎	◎	◎ *1	○ *1	◎
Engine Oil	◎	◎	◎	◎	◎
Break Fluid	×	×	◎	○	×
Coolant	◎	◎	◎	◎	◎
ATF	◎	◎	◎	◎	◎

Note : *This table is based on our research and the results may change depending on the actual conditions.

It is recommended to perform a pre-evaluation under a condition equal to an actual use condition.

*Please do not store the products with leftover liquid. It may cause cracks.